




ISO 9001:2008 REGISTERED

---

**MBT**

**Chemical Name: 2-Mercaptobenzothiazole**

### Structure



**Molecular Weight: 167.3**

**Class: Thiazole**

**CAS#: 149-30-4**

MBT is a semi-fast, non-staining general purpose accelerator for dry rubber and latex compounding. MBT has a low activation temperature and becomes very scorchy above 176°C (240°F). MBTS can be used to replace MBT if improved scorch behavior is desired. MBT allows for good aging properties. In order to achieve faster cure and higher modulus, secondary accelerators can be used; i.e. ZBEC, ZDEC, TBzTD, or TMTD. MBT is a viable option when compounding needs to involve non-nitrosamine generating accelerators.

MBT has typical properties of: Specific Gravity @ 1.47; Melt Point @ 173°C, and is available in a light yellow oil treated powder or granular form.

12/23/14

---

HARWICK STANDARD MAKES NO WARRANTIES, EXPRESS OR IMPLIED, WITH RESPECT TO THE GOODS OR USES OF THE GOODS OR PERFORMANCE OF THE GOODS AND MAKES NO WARRANTIES OF THE FITNESS FOR PARTICULAR PURPOSE OR MERCHANTABILITY. BUYER ACKNOWLEDGES THAT HARWICK STANDARD WILL NOT BE LIABLE FOR CONSEQUENTIAL, INCIDENTAL, DIRECT OR SPECIAL DAMAGES ARISING, DIRECTLY OR INDIRECTLY, IN RESPECT TO SUCH GOODS OR THE USE OR FAILURE THEREOF, WHETHER BASED ON BREACH OF WARRANTY, NEGLIGENCE, STRICT LIABILITY IN TORT OR OTHERWISE.

### **HARWICK STANDARD DISTRIBUTION CORPORATION**

60 S. SEIBERLING ST. • P.O. BOX 9360 • AKRON, OH 44305-0360 • U.S.A.  
PHONE: (330) 798-9300 • FAX: (330) 798-0214  
WWW.HARWICKSTANDARD.COM