

## ADVALUBE™ B-3314 Specialty Lubricant

### Description

ADVALUBE B-3314 is a combination of lubricants with different polarities, giving a balanced lubrication.

### Applications

- General purpose Vinyl profiles
- Vinyl window profiles

### Benefits

- Based on internal, external and balanced lubricants
- Allows glossy and smooth surfaces to be obtained
- Can be used as sole lubricant in the Vinyl formulation
- Provides a very broad processing window

### Typical Dosage

1.5 – 3.0 phr

### Typical Properties

Melting Range	105–115°C
Bulk Density	0.540 g/ml

### Appearance

Ivory-colored powder

### Packaging

55 lb. (25 kg) PE bags on 2200 lb. pallets (other packaging available)

### Regulatory Status

FDA	N
NSF	N
Kosher	N
TSCA	Y
DSL	Y
EINECS	Y

### Shelf Life

24 Months

### Storage

Store in cool, dry, well-ventilated area.

## Transfer

Follow good manufacturing and handling practices as well as the practices in the Material Safety Data Sheet (MSDS).

## MSDS's

Material Safety Data Sheets (MSDS) are available, outlining hazards and safe handling methods. Contact Rohm and Haas for copies of the MSDS for this product and for other handling information.

### Vinyl Window Profile Formulation

Vinyl Resin (K = 66-67; i.v. = 0.92)	100 PHR
ADVASTAB TM-181	1.2
Calcium Stearate	0.8
Paraffin Wax (165°F)	0.5
ADVALUBE B-3310	1.0
ADVALUBE E-2100	0.6
Oxidized Polyethylene	0.15
PARALOID K-120ND	1.0
PARALOID K-175	0.5
PARALOID KM-334	5.0
TiO <sub>2</sub>	9.0
CaCO <sub>3</sub> (Ultra-Fine)	5.0

#### ALTERNATIVE IMPACT MODIFIER:

PARALOID KM-399 @ 4.0 phr

#### ALTERNATIVE MULTI-FUNCTIONAL ADDITIVE SELECTIONS:

PARALOID KM-940 @ 6.5 phr or  
PARALOID KM-346 @ 5.0 phr

#### ALTERNATIVE TIN STABILIZERS:

ADVASTAB TM-186 - Thioglycolate for lower level usage  
versus TM-181 for better early color  
TM-286SP - Highest efficiency reverse ester  
TM-281SP - Low cost best efficiency at low levels

#### ALTERNATIVE LUBRICANT PACKAGE:

ADVALUBE B-3314 2.7 with 0.5 phr ADVAWAX 280

### Vinyl Window Profile (High Gloss)

Vinyl Resin (K = 66-67; i.v. = 0.92)	100 PHR
ADVASTAB TM-186	1.2
Calcium Stearate	1.5
ADVAWAX 280	1.7
Oxidized Polyethylene	0.1
PARALOID K-120ND	1.0
PARALOID KM-399	4.5
TiO <sub>2</sub>	9.0
CaCO <sub>3</sub> (Ultra-Fine)	3.0

#### ALTERNATIVE IMPACT MODIFIERS:

PARALOID KM-346 @ 5.0 phr  
PARALOID KM-334 @ 5.5 phr  
PARALOID KM-940 @ 5.5 phr

**ALTERNATIVE TIN STABILIZERS:**

- ADVASTAB TM-181 - Equivalent performance to TM-186 at this level
- TM-281SP - Low cost - high efficiency at low levels  
(reverse ester)
- TM-286SP - High efficiency at all levels (reverse ester)

---

**ALTERNATIVE LUBRICANT SYSTEMS** (in place of CaSt, ADVAWAX 280 and Oxidized Polyethylene):

1. CaSt (1.0)/ Paraffin Wax (165°F) (0.6)/ ADVALUBE B-3310 (0.6)/ ADVALUBE F-1005 (0.4)/ADVAWAX 280 (0.5)
  2. ADVALUBE B-3314 (2.6)/ ADVAWAX 280 (0.5)
- 

---

Rohm and Haas Company is a raw materials supplier, not an end-use manufacturer of product. Development of a final formulation, testing, application, and ultimate performance of the end-use product is fully the responsibility of the formulator.

These suggestions and data are based on information we believe to be reliable. They are offered in good faith but, as conditions and methods of use of our products are beyond our control, Rohm and Haas Company makes no warranties, either expressed or implied, concerning the final end-use product. Rohm and Haas Company expressly disclaims any implied warranty of fitness for a particular purpose. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them on a commercial scale.

Suggestions for uses of our product or the inclusion of descriptive material from patents and the citation of specific patents in this publication should not be understood as recommending the use of our products in violation of any patent, or as permission or license to use any patents of the Rohm and Haas Company.

PARALOID, PARALOID EXL, ADVASTAB, ADVAWAX, ADVALUBE, ADVAPAK, ADVAFLEX, VINYZENE, Bio-Pruf, and Bio-Pruf TREATED are trademarks of Rohm and Haas Company or of its subsidiaries or affiliates.

