

TECHNICAL DATA SHEET

Iron Oxide Black BK5099

Edition of	2012-12-11
Type	Black Pigment-High Performance micronised
Molecular formula	Fe ₃ O ₄
Molecular weight	231.54
Delivery Form	Powder
Chemical Class	Synthetic Iron Oxide Fe ₃ O ₄
Color Index	Pigment Black 11 (77499)
CAS No.	1317-61-9
Use ReCommedation	Coating, Construction, Plastic

COLOR VALUES AND TINTING STRENGTH

Reference			Standard: DIN 6174
	Min	Max	Test Method
Reduction with titanium dioxide (1:5)	R-706		No.038.2009-08-01
ΔL*	-0.5	0.5	
Δa*	-0.5	0.5	
Δb*	-0.5	0.5	
ΔE*ab		0.8	
Binder	R-05		
Relative tinting strength [%]	97.0	103.0	No.038.2009-08-01

TECHNICAL DATA

	Min	Max	Test Method
Fe ₃ O ₄	94		DIN 55913-2
Water soluble substances [%]		0.5	DIN ISO 787-3
Moisture at 105°C [%]		0.5	DIN ISO 787-2
Oil absorption approx [%]	25		DIN ISO 787-5
Sieve residue on 0.045mm mesh [%]		0.05	DIN 53195
Tinting strengths vs. standard range	97	103	DIN 6174
ΔE		0.8	DIN 6174
PH Value	7.0	8.0	DIN ISO 787-9
Density		4.5	DIN ISO 787-10
Tamped Density		1.0	DIN ISO 787-11

STANDARD PACKAGING 25kg/bag

TRANSPORT AND STORAGE

Protect against weathering. Store in a dry place and avoid extreme fluctuations in temperature. Special conditions for opened packaging: Close bags after use to prevent the absorption of moisture and contamination.

SAFETY

The product is not classified as dangerous under the relevant EC directives and corresponding national regulations valid in the individual EU member states. It is not dangerous according to transport regulations. In countries outside the EU, compliance with the respective national legislation concerning the classification, packaging, labeling and transport of dangerous substances must be ensured.

The information contained in the safety data sheet should be observed.

This contains information on handling, product safety and ecology.