

TECHNICAL DATA SHEET

Iron Oxide Orange 960

Edition of	2012-12-20
Type	Yellow Pigment
Molecular formula	Fe ₂ O ₃ . H ₂ O
Molecular weight	177.71
Delivery Form	Powder
Chemical Class	Synthetic Iron Oxide
Color Index	Pigment Yellow 42(77492)
CAS No.	20344-49-4
Use ReCommedation	Coatings

COLOR VALUES AND TINTING STRENGTH

Reference			Standard: DIN 6174
	Min	Max	Test Method
Reduction with titanium dioxide (1:2)	R-706		No.038.2009-08-01
△L*	-0.7	0.7	
△a*	-0.7	0.7	
△b*	-0.7	0.7	
△E*ab		1.0	
Binder	R-05		
Relative tinting strength [%]	95	105	No.038.2009-08-01

TECHNICAL DATA

	Min	Max	Test Method
Fe ₂ O ₃	88		DIN 55913-2
Water soluble substances [%]		0.5	DIN ISO 787-3
Moisture at 105°C [%]		1.0	DIN ISO 787-2
Oil absorption approx [%]	35		DIN ISO 787-5
Sieve residue on 0.045mm mesh [%]		0.1	DIN 53195
Color compared with standard	Similar-a little(95 - 105)		DIN 6174
ΔE		1.0	DIN 6174
PH Value	3.5	7.5	DIN ISO 787-9
Loss on Heating 1000°C 1/2h		14.0	DIN 55913-2
Density		4.0	DIN ISO 787-10
Tamped Density		0.6	DIN ISO 787-11

STANDARD PACKAGING 20kg/bag

TRANSPORT AND STORAGE

Protect against weathering. Store in a dry place and avoid extreme fluctuations in temperature. Special conditions for opened packaging: Close bags after use to prevent the absorption of moisture and contamination.

SAFETY

The product is not classified as dangerous under the relevant EC directives and corresponding national regulations valid in the individual EU member states. It is not dangerous according to transport regulations. In countries outside the EU, compliance with the respective national legislation concerning the classification, packaging, labeling and transport of dangerous substances must be ensured.

The information contained in the safety data sheet should be observed.

This contains information on handling, product safety and ecology.