



ISOLENE® 400-S

ISOLENE® 400-S is a low molecular weight liquid polymer derived from synthetic polyisoprene rubber. It offers the performance and processing characteristics of natural rubber with the added benefit of lighter color and none of the natural impurities inherent in natural rubber products.

ISOLENE® 400-S is a high viscosity liquid at room temperature. It is a translucent, honey-colored liquid in bulk form and virtually clear in a thin film.

Technology / Base	Polyisoprene
Type of Product	Elastomer
Appearance / Color	Light Amber
Typical Viscosity Range	300,000 to 500,000 cps @ 38°C
Consistency	Liquid

Features and Benefits

ISOLENE® 400-S provides many performance properties in adhesive formulations and other compounds.

- Softens the resin
- Improves low-temperature tack
- Improves the resistance to bleed through
- Acts as an efficient vehicle for powdered additives and curatives into a rubber compound
- ISOLENE® liquid synthetic rubber cures by the same mechanism as polyisoprene rubber. It can replace rubber 1:1. A slight increase in curative levels may provide optimum performance when using levels above 15-20 phr of ISOLENE®.

Recommended For

ISOLENE® 400-S is ideal for pressure sensitive adhesive (PSA) formulations based on block copolymers.

Typical applications include the following:

- Rubber and polymer processing aid.
- Reactive vehicle for powdered additives.
- Rheology modifier for lubricants.
- Polymer base for molding and tooling systems.
- Polymer base for electrical encapsulants.
- Production of pressure sensitive adhesives.

H.B. Fuller offers a Compounding Guide with starting point formulas for these and other applications.

Handling

ISOLENE® products are viscous polymers. Heating the drums lowers the viscosity for easier handling. Vent the drums before heating to avoid pressure build up.

Avoid exposing ISOLENE® products to temperatures above 121°C (250°F). The polymer may form a skin and it may darken.

ISOLENE® polymers can be compounded with virtually any type of rubber processing equipment. Processing requirements vary with the desired finished properties and with the other formulation ingredients

Storage and Shelf Life

Store in a dry environment to prevent damage to the packaging. The liquid rubber products are stable over a wide temperature range. They are not damaged by freezing temperatures or occasional short-term exposure to temperatures of 66°C (150°F). The shelf life is a minimum of two years if stored properly in an unopened container.



Typical Packaging

ISOLENE® 400-S is available in the following standard packages:

- 330 Lb. steel drum

Safety and Disposal

Prior to working with this or any product consult product label and Safety Data Sheet (SDS) for necessary health and safety precautions.

Technical Data

Property	Typical Value	Test Method
Specific Gravity	0.92	ASTM D1875
Density (lb/gal)	7.7	ASTM D1875
Avg Molecular Wt.	65,000	GPC
Volatiles (Wt %)	0.47	ASTM D1416
Ash (Wt %)	0.1	ASTM D1416
Unsaturation (Mole %)	92	Ozone Analysis
Solids (%)	100	
Color, Gardner	8 Max	Visual
Glass transition temp. (Tg. °C)	-65	

Viscosity

ISOLENE® 400-S is a low molecular weight grades of synthetic polyisoprene. They are viscous liquids at typical processing temperatures. The following table indicates the viscosity (cp) at typical conditions.

Temperature	Viscosity (cP)
25°C/77°F	1,000,000
38°C/100°F	380,000
52°C/125°F	170,000
66°C/150°F	110,000
80°C/175°F	50,000
93°C/200°F	23,000
121°C/250°F	13,000
149°C/300°F	8,000

H.B. Fuller Company
 4401 Page Ave
 Michigan Center, MI 49254
 Tel: +1.800.248.4011

Connecting what matters.™

ISOLENE® 400-S TDS_EN 20200102

www.hbfuller.com

www.hbfullerengineering.com

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience, and we believe this information to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

® and ™ are trademarks of H.B. Fuller Company or one of its affiliated entities.



NOTE TO USER: by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

H.B. Fuller
www.hbfuller.com

©H.B. Fuller Company, 2018