

PERBUNAN[®] 3470 F

Grade Name	PERBUNAN [®] 3470 F
Product Description	Butadiene-acrylonitrile copolymer, non-staining stabilized
Supply Form	Bales

Specifications¹

Characteristics	Limits	Unit	Testing Method
Mooney Viscosity ML (1+4) 100°C without pre-treatment	70 ± 7	MU	ISO 289/ASTM D 1646
Acrylonitrile content	34 ± 1.0	wt %	ISO 24698-1
Volatile matter	≤ 0.7	wt %	ISO 248/ASTM D 5668

¹For each delivery a Certificate of Analysis (CoA) will be sent, which contains the actual measured values of the specified properties for each batch.

Specific gravity	0.97															
Cure characteristics	<p>Test formulation according to ISO 4658 - Miniature internal mixer (based on IRB 7)</p> <p>MDR 160°C, micro-dies; ± 0.5 degree arc, 30 min running time no preheat</p> <table> <thead> <tr> <th>Property</th> <th>Value</th> <th>Test method</th> </tr> </thead> <tbody> <tr> <td>ML</td> <td>2.4 ± 0.7 dNm</td> <td>ISO 6502</td> </tr> <tr> <td>MH</td> <td>22.0 ± 2.5 dNm</td> <td>ISO 6502</td> </tr> <tr> <td>t'10</td> <td>2.2 ± 0.7 min</td> <td>ISO 6502</td> </tr> <tr> <td>t'90</td> <td>6.4 ± 1.6 min</td> <td>ISO 6502</td> </tr> </tbody> </table>	Property	Value	Test method	ML	2.4 ± 0.7 dNm	ISO 6502	MH	22.0 ± 2.5 dNm	ISO 6502	t'10	2.2 ± 0.7 min	ISO 6502	t'90	6.4 ± 1.6 min	ISO 6502
Property	Value	Test method														
ML	2.4 ± 0.7 dNm	ISO 6502														
MH	22.0 ± 2.5 dNm	ISO 6502														
t'10	2.2 ± 0.7 min	ISO 6502														
t'90	6.4 ± 1.6 min	ISO 6502														

PERBUNAN[®] 3470 F

Packaging	25 kg bales wrapped in dispersable PE-film (Vicat point: 85°C / ISO 306)
Shelf life	24 month from date of production at temperatures not exceeding 35°C in dry conditions; exposure to light has to be avoided
Product Safety	Relevant safety data and references as well as the possibly necessary warning labels are to be found in the safety data sheet.

PERBUNAN[®] is a Registered Trademark of ARLANXEO Deutschland GmbH

This information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided – especially that contained in our safety data and technical information sheets – and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Issue number: LXS 04 / Date of issue: January 01, 2010 / Previous issue from April 13, 2007 / Information current as of date of issue. Please contact your ARLANXEO representative to determine if this publication has been revised.