




FLEXSYS



Product Data

PERKACIT SDBC

Sodium dibutyldithiocarbamate

CAS Reg. No.: 136-30-1

Molecular weight: 227

FUNCTION

Perkacit SDBC is used as an accelerator in combination with thiurams, thiazoles and guanidines in the vulcanization of NR and SBR latices.

MAJOR APPLICATIONS AND PROPERTIES

- The aqueous solution of Perkacit SDBC is highly suitable for use in NR and SBR latices resulting in vulcanization initiation from 90°C-100°C.
- Activation of Perkacit SDBC is possible with thiazoles, thiurams and guanidines.
- Perkacit SDBC increases the viscosity of latex compounds very rapidly.
- It should be noted that in the application of Perkacit SDBC N-nitrosodibutylamine can be formed by the reaction of dibutylamine, a decomposition product, with nitrosating agents (nitrogen oxides).
- Perkacit SDBC is regulated for use in articles in contact with food as specified under FDA 21 CFR 177.2600 and under BgVV XXI, Category 1 (latex only) and Categories 2-4.

COMPOUNDING INFORMATION

When used as a primary accelerator Perkacit SDBC levels of 1.0 - 3.0 phr are common.

When used as a secondary accelerator dosages of 0.25 - 1.0 phr are normal.

In general Perkacit SDBC closely resembles Perkacit ZDBC in its applications.

Accelerators

MARKETED BY
**HARWICK STANDARD
DISTRIBUTION CORPORATION**
60 S. Seiberling Street • Akron, Ohio 44305

HANDLING PRECAUTIONS

For detailed information on toxicological properties and handling precautions please refer to the current Safety Data Sheet. This information sheet can be downloaded from our web site or requested from the nearest Flexsys office and should be consulted before handling this product.

STORAGE RECOMMENDATIONS

Store Perkacit SDBC in a cool, dry, well ventilated area, avoiding exposure of the packaged product to direct sunlight.

PRODUCT INFORMATION

Perkacit SDBC Product form	liq-W47% 47% solution in water	
<u>PRODUCT SPECIFICATIONS</u>		<u>Test method</u>
Appearance	pale yellow green to light brown liquid	FF97.5
Assay (%)	45.5-47.5	FJo83.4
pH value	9.0-11.0	FF83.11
<u>TYPICAL PROPERTIES</u>		
Density at 20 °C (kg/m ³)	1050-1070	

MARKETED BY
**HARWICK STANDARD
DISTRIBUTION CORPORATION**
60 S. Seiberling Street • Akron, Ohio 44305

For further information please contact your local Flexsys office or regional Flexsys headquarters:

Regional Headquarters	:	Brussels	Akron	Singapore
Tel.	:	+32 2 714 32 11	+1 330 666 41 11	+65 872 28 08
Fax	:	+32 2 714 32 32	+1 330 668 83 45	+65 872 28 18

All product names are registered trade marks.

SDBC2.AC/1000

The information and recommendations in this publication are provided without warranty as to completeness, correctness or suitability for any particular purpose. The user of this publication assumes responsibility for and Flexsys shall not be liable for any injury, loss or damage arising from any use or reliance upon its contents.

©Copyright Flexsys 2000.

page 2 of 2