



Product Data

PERKACIT SDMC

Sodium dimethyldithiocarbamate

CAS Reg. No.: 128-04-1

Molecular weight: 143

FUNCTION

Perkacit SDMC is used as an accelerator in the vulcanization of NR and SBR latices. It is also used as a radical inhibitor in the polymerization of SBR.

MAJOR APPLICATIONS AND PROPERTIES

- The aqueous solution of Perkacit SDMC is highly suitable for use in NR and SBR latices initiating the vulcanization from 80°C - 100°C.
- Perkacit SDMC is used as a radical inhibitor (short-stop) in the final stage of the SBR polymerization.
- It should be noted that in the application of Perkacit SDMC N-nitrosodimethylamine can be formed by the reaction of dimethylamine, a decomposition product, with nitrosating agents (nitrogen oxides).
- Perkacit SDMC is regulated for use in articles in contact with food as specified under FDA 21 CFR 177.2600, 175.105, 176.300 and under BgVV XXI, Category 1(latex only) and Categories 2-4.

COMPOUNDING INFORMATION

As an accelerator in NR latex, amounts of 1.0 phr Perkacit SDMC in combination with 2.5 phr sulfur are suggested as a good starting point.

In SBR foamed applications 1.5 phr Perkacit SDMC in combination with 1.0 phr Perkacit ZMBT and 2.5 phr sulfur are suggested as a good starting point.

When used as a short stopper for SBR typical amounts of Perkacit SDMC are 0.2% (on a 100% activity basis) based on SBR polymer weight.

MARKETED BY
**HARWICK STANDARD
DISTRIBUTION CORPORATION**
60 S. Seiberling Street • Akron, Ohio 44305

HANDLING PRECAUTIONS

For detailed information on toxicological properties and handling precautions please refer to the current Safety Data Sheet. This information sheet can be downloaded from our web site or requested from the nearest Flexsys office and should be consulted before handling this product.

STORAGE RECOMMENDATIONS

Store Perkacit SDMC in a cool, dry, well ventilated area, avoiding exposure of the packaged product to direct sunlight.

PRODUCT INFORMATION

Perkacit SDMC Product form	liq-W41% 41% solution in water	
<u>PRODUCT SPECIFICATIONS</u>		<u>Test method</u>
Appearance	light yellow liquid	FF97.5
Color (Gardner) (Gardner) max.	3	FCol83.3
Assay (%)	40.0-42.0	FJo83.4
pH value (1% aqueous solution)	9.5-10.5	FF91.3
<u>TYPICAL PROPERTIES</u>		
Density at 20°C (kg/m ³)	1170-1190	

MARKETED BY
**HARWICK STANDARD
DISTRIBUTION CORPORATION**
60 S. Seiberling Street • Akron, Ohio 44305

For further information please contact your local Flexsys office or regional Flexsys headquarters:

Regional Headquarters	:	Brussels	Akron	Singapore
Tel.	:	+32 2 714 32 11	+1 330 666 41 11	+65 872 28 08
Fax	:	+32 2 714 32 32	+1 330 668 83 45	+65 872 28 18

All product names are registered trade marks.

SDMC3.AC/1000

The information and recommendations in this publication are provided without warranty as to completeness, correctness or suitability for any particular purpose. The user of this publication assumes responsibility for and Flexsys shall not be liable for any injury, loss or damage arising from any use or reliance upon its contents.

©Copyright Flexsys 2000.

page 2 of 2