



NATROCHEM INC.
P.O. BOX 1205
SAVANNAH, GA 31402
(912) 236-4464 FAX: (912) 236-1919

DATA SHEET **TAC DLC®-A-50**

TAC DLC-A-50 is a blend of triallyl cyanurate and silica. It is a coagent for peroxide cured EP polymers and functions as an accelerator for EPM. Reduces cure time, eliminates odor caused by sulfur coagent, and improves heat aging and compression set resistance.

TEST	TEST METHOD	SPECIFICATION
Actives Content, %	QCL4.10-3-1	48 - 52
Carrier Content, %	QCL4.10-3-1	48 - 52
Appearance	Visual	Off-white to tan powder

TYPICAL PROPERTIES:

Actives Content, %	50
Carrier Content, %	50
Specific Gravity (Apparent)	1.28
Packaging	30# Net Multi-wall Bags
Color	Off White

Date of Revision: 12/12/2014

The information in this data sheet is derived from the best available sources and is believed to be accurate. However, no guarantee is expressed or implied regarding the accuracy of these data or the use of this product, nor are any statements in this bulletin intended as recommendations to use our products in the infringement of any patents.

OTHER NATROCHEM PRODUCTS

**DLC® s - Galex® - Rosin Oils - Rosin Pitches - Tarenes™
Natro-Flex™ - Tar-Cel® - Natro-Cel®**