



NATROCHEM, INC.
P.O. BOX 1205
SAVANNAH, GA 31402
(912) 236-4464 FAX: (912) 236-1919
www.natrochem.com

DATA SHEET TARENE™ 14

Tarene 14 is a low-cost, dark, non-staining, thermoplastic oleo-resinous product having a naval stores base. The performance properties are comparable to, or superior to, pine tar. Tarene 14 finds its widest application as plasticizer, tackifier, and processing aid in rubber compounding. Other potential uses include adhesives, tar modifications, epoxy extension, coatings, mastics, and use as a low cost acid for emulsions.

TEST	TEST METHOD	SPECIFICATION
Acid Number	QCL-8.2.4-2-4	50 - 60
Viscosity, SFS @ 122°F	QCL-8.2.4-2-5	90 - 150
Specific Gravity @ 80°F	QCL-8.2.4-2-12	0.950 - 1.000
Moisture, %	QCL-8.2.4-2-7	1.0 Max
Heat Loss, 2 hrs @ 105°C	QCL-8.2.4-2-9	7.0 Max
Ash, %	QCL-8.2.4-2-8	1.0 Max

TYPICAL PROPERTIES

Acid Number	52
Viscosity, SFS @ 122°F	120
Specific Gravity @ 80°F	0.975
Moisture, %	0.1
Heat Loss, %	2.0
Ash, %	0.3

Date of Revision: 12/27/02

The information in this data sheet is derived from the best available sources and is believed to be accurate. However, no guarantee is expressed or implied regarding the accuracy of these data or the use of this product, nor are any statements in this bulletin intended as recommendations to use our products in the infringement of any patents.

OTHER NATROCHEM PRODUCTS

DLC® - Galex® - Rosin Oils - Rosin Pitches - Tarene™
Natro-Flex™ - Tar-Cel® - Natro-Cel®